



Evaluation Listing CCMC 13527-L Foamsulate™ ECO

MasterFormat:	07 21 19.02
Evaluation issued:	2011-02-01
Re-evaluated:	2017-09-06
Re-evaluation due:	2020-02-05

1. Evaluation

The product conforms to CAN/ULC-S705.1-01, "Thermal Insulation – Spray Applied Rigid Polyurethane Foam, Medium Density – Material – Specification," including Amendments 1 and 2. The product's classification, minimum field density, long-term thermal resistance (LTTR), water vapour permeance (WVP) and the time-to-occupancy values are provided in Table 1.1.

Table 1.1 Classification, Field Density, LTTR, WVP and Time-to-Occupancy Specifications for the Product

Product	Classification	Minimum Field Density ¹ (kg/m ³) [lb/ft ³]	50 mm Design LTTR (m ² oC/W)	50 mm WVP ² (ng/(Pa·s·m ²))	Time-to-Occupancy ³ (day)
Foamsulate™ ECO	Type 2	37 [2.30]	2.00	58	1

Notes to Table 1.1:

- Based on the qualification testing to CAN/ULC-S705.1, the specified minimum field density must comply with CAN/ULC-S705.1, as measured on-site in accordance with CAN/ULC-S705.2-05, "Thermal Insulation – Spray Applied Rigid Polyurethane Foam, Medium Density – Application."
- The WVP is determined from a core sample with the skin removed. Due to the effect of the skins, the WVP at this thickness would be lower in the field-installed product.
- For retrofit construction, the time to occupancy is one (1) day when the segregated retrofit area is ventilated as required by CAN/ULC-S705.2 during installation of the product. See Note 3 of Table 1 in the Annex for the product for further details.

2. Description

The product is a closed-cell, spray-applied, rigid polyurethane foam of medium density. The foam system consists of two components that must be labelled as follows along with "CCMC 13527-L:"

- Isocyanate (Component A): Foamsulate™; and
- Resin (Component B): Foamsulate™ ECO.

The two components are mixed on-site by an Accella-qualified installer (see Section 3.1) with fixed-ratio positive displacement equipment. The colour of the installed final cured product is Georgian Pine green.

3. Standard and Regulatory Information

See the Annex appended to this Listing, which summarizes the product standard.

This product was evaluated to the product standard referenced in the Annex current as of 2011-04-13. Note that the Annex may have been updated since this Listing was issued to include more recent editions of the applicable product standard. Therefore, this Listing may not reflect the requirements contained in any updated version of this product standard.

3.1 Qualified Installers

This is a site-manufactured product whereby Accella Polyurethane Systems Canada, Inc. requires that only specific, qualified installers be authorized to install their proprietary spray-polyurethane insulation in buildings. In accordance with the Accella Polyurethane Systems Canada, Inc. field quality assurance program (FQAP), Morrison Hershfield (MH) has been commissioned to license the specified installers and issue the requisite MH identification card to them. All specified installers must have an MH identification card.

3.2 Third-Party Field Auditing of Qualified Installers

As part of their FQAP, Accella Polyurethane Systems Canada, Inc. also stipulates that field-audit inspections be conducted by field inspectors licensed by MH. Upon completion of the field audit, MH will report the product's conformity results and any corrective action, if necessary, to Accella Polyurethane Systems Canada, Inc. Building officials who would like field-audit inspections to be conducted on specific building sites can contact MH at:

Morrison Hershfield
Suite 600, 235 Yorkland Boulevard
Toronto, ON M2J 1T1

Telephone: 800-796-5792

Web site: www.morrisonhershfield.com

Listing Holder

Accella Polyurethane Systems Canada, Inc.
1000-840 Howe Street
Vancouver, BC V6Z 2S9

Telephone: 604-687-2242

Web site: www.premiumspray.ca

Field-Finished Product

The foam insulation is a site-manufactured product.

Plant(s)–Raw Materials

Marietta, GA, USA

Disclaimer

This Listing is issued by the Canadian Construction Materials Centre, a program of NRC Construction at the National Research Council of Canada. The Listing must be read in the context of the entire CCMC Registry of Product Evaluations.

Readers must confirm that the Listing is current and has not been withdrawn or superseded by a later issue. Please refer to http://www.nrc-cnrc.gc.ca/eng/solutions/advisory/ccmc_index.html, or contact the Canadian Construction Materials Centre, NRC Construction, National Research Council of Canada, 1200 Montreal Road, Ottawa, Ontario, K1A 0R6. Telephone: 613-993-6189. Fax: 613-952-0268.

NRC has evaluated the material, product, system or service described herein only for those characteristics stated herein. The information and opinions in this Listing are directed to those who have the appropriate degree of experience to use and apply its contents. This Listing is provided without representation, warranty, or guarantee of any kind, expressed, or implied, and the National Research Council of Canada (NRC) provides no endorsement for any evaluated material, product, system or service described herein. NRC accepts no responsibility whatsoever arising in any way from any and all use and reliance on the information contained in this Listing. NRC is not undertaking to render professional or other services on behalf of any person or entity nor to perform any duty owed by any person or entity to another person or entity.

Date modified:

2017-09-06



Spray-Applied Rigid Polyurethane Foam Insulation, Medium Density [Annex]

MASTERFORMAT: 07 21 19.02

Issued: 2011-04-13

Scope

These Evaluation Listings apply to spray-applied rigid polyurethane foam, medium density, intended for use as thermal insulation for both building and non-building applications, whether applied on a building site or in a prefabrication (manufacturing) process. This material is also known as foamed in-situ insulation. The continuous-use temperature is within the range -60°C to $+80^{\circ}\text{C}$.

The proponent has demonstrated that the product meets the following standard (see Table 1 for the performance requirements):

- CAN/ULC-S705.1-01 (including Amendments 1 and 2), “Standard for Thermal Insulation – Spray Applied Rigid Polyurethane Foam, Medium Density – Material – Specification”; or
- CAN/ULC-S705.1-01 (including Amendments 1, 2 and 3), “Standard for Thermal Insulation – Spray Applied Rigid Polyurethane Foam, Medium Density – Material – Specification.”

Spray-applied rigid polyurethane foam, medium density, must be installed by a licensed installer in accordance with the manufacturer’s instructions and the following standard:

- CAN/ULC-S705.2-05, “Standard for Thermal Insulation – Spray Applied Rigid Polyurethane Foam, Medium Density – Application.”

For compliance to CAN/ULC-S705.2, users should contact the third-party organization that has been identified by the foam manufacturer as the third party operating the field quality assurance program (FQAP) for the foam product (see product listing).

Standard

Table 1. Technical Requirements for Physical Properties

Property	Unit	Requirement		
		Minimum	Maximum	
Air permeance (mandatory material testing)	L/s @ 75 Pa	No min.	0.02	
Air permeance (optional system testing)	L/s @ 75 Pa	No min.	0.05	
Apparent core density	kg/m ³	28	No max.	
Compressive strength	kPa	170	No max.	
Dimensional stability volume change at:	-20°C	%	No min.	-1
	80°C	%	-1	8
	70°C, 97 ± 3% RH	%	No min.	14
Surface burning characteristics – flame spread	–	No min.	500 ¹	
Open-cell content volume	%	No min.	8	
Initial thermal resistance of a 50-mm-thick specimen after 3 days at 23 ± 2°C	m ² ·°C/W	2.5	No max.	
Conditioned thermal resistance of a 50-mm-thick specimen after:	180 days at 23 ± 2°C, or	m ² ·°C/W	Declare ²	No max.
	90 days at 60 ± 2°C			
Long-term thermal resistance of a 50-mm-thick specimen – Type 1	m ² ·°C/W	1.8	No max.	
Long-term thermal resistance of a 50-mm-thick specimen – Type 2	m ² ·°C/W	2.0	No max.	
Tensile strength	kPa	200	No max.	
Volatile organic emissions	–	Pass ³	No max.	
Water absorption by volume	%	No min.	4	
Water vapour permeance of a 50-mm-thick specimen	ng/(Pa·s·m ²)	No min.	60	

Notes to Table 1:

- ¹ Results are valid for qualification to the standard. As noted in the standard, “for building code purposes, the flame-spread rating shall be conducted in accordance with the code-specified flame-spread test details with respect to the number of specimens to be tested, specimens tested intact and cut specimens.”
- ² This requirement is only referenced in CAN/ULC-S705.1-01 (with Amendments 1 and 2).
- ³ “Pass” means that after 30 days the volatile compound emissions do not exceed the maximum indoor air concentration stated in Table 2 of CAN/ULC-S705.1. In cases of retrofit construction (e.g., occupied buildings), CAN/ULC-S705.2 requires that the ventilation rate be no less than 0.3 air changes per hour within the working area during the application of the product and that the working area be isolated during spraying. The same ventilation rate is required after the product has been sprayed and for the time period determined in accordance with CAN/ULC-S705.1. See the product listing for the time period required before occupancy.

Labelling

In compliance with CAN/ULC-S705.1-01 (with Amendments 1 and 2), each liquid component container must be identified as either the polyisocyanate component (“A”) or the resin component (“B”). Unless otherwise specified, each container must be marked with the following information:

- manufacturer’s name;
- product name;
- type of material (e.g., insulation);
- net mass of the contents of the packaged material;
- country of manufacture;
- lot number;
- date of manufacture;
- “use before” date;
- the means to identify the installed product; and
- the phrase “CAN/ULC-S705.1” indicating conformance to the standard.

In compliance with CAN/ULC-S705.1-01 (with Amendments 1, 2 and 3), each liquid component container must be identified as either the polymeric isocyanate component (“A”) or the resin component (“B”). The polymeric isocyanate component must be marked with the following information:

- manufacturer’s name;
- product name;
- type of material (e.g., insulation);
- net mass of the contents of the packaged material;
- country of manufacture;
- lot number; and
- date of manufacture.

The resin component must be marked with the following information:

- manufacturer’s name;
- product name;
- type of material (e.g., insulation);
- net mass of the contents of the packaged material;
- country of manufacture;
- lot number;
- date of manufacture;
- “use before” date;
- the means to identify the installed product;
- the phrase “CAN/ULC-S705.1” indicating conformance to the standard; and
- LTTR (50 mm) RSI result.

National Building Code of Canada (NBC)

NBC References

CAN/ULC-S705.1-01 is referenced in Table 5.10.1.1. and Clause 9.25.2.2.(1)(g) of Division B of the NBC 2010.

CAN/ULC-S705.2-05 is referenced in Sentence 5.3.1.3.(3), Table 5.10.1.1., and Sentence 9.25.2.5.(1) of Division B of the NBC 2010.